

SUPRAdisc™ AKS 4 Modules For Color and Flavor Correction


SUPRAdisc AKS 4 Modules

SUPRAdisc AKS 4 modules were developed to satisfy general purpose carbon adsorption applications in the food and beverage industry.

Description

Powdered activated carbon (PAC) is widely used in the food and beverage industry for adsorption applications. The use of bulk PAC has significant drawbacks relating to the handling of bulk carbon powder, cleaning of the process equipment, as well as time and costs associated with carbon removal from the process.

SUPRAdisc AKS 4 Modules alleviate these concerns by incorporating activated carbon within a matrix of cellulosic fibers. This immobilized carbon media is coupled with a downstream protective filter paper to prevent any possible carbon particle shedding downstream of the filter. Additionally, the adsorption efficiency of Seitz AKS immobilized carbon filter media is greater than an equivalent amount of bulk powdered activated carbon (PAC), reducing overall process time and increasing product yield. An internal comparative study using the same carbon grade showed up to 150 % better color removal efficiency when compared to bulk PAC.



SUPRAdisc AKS 4 Modules

Features	Benefits
Carbon-impregnated media with a homogeneous and consistent matrix	<ul style="list-style-type: none"> • Free of carbon dust • Simplified handling and cleaning • When using protection paper downstream, no further trap filtration required
High adsorption efficiency as compared to PAC	<ul style="list-style-type: none"> • Reduction of overall process time • Increased product yield • Good permeability with excellent filtrate quality
General-duty media targeted to food and beverage industry needs	<ul style="list-style-type: none"> • High economic efficiency due to a long service life

Quality

- Filter sheets produced in a controlled environment
- Manufactured according to ISO 9001:2008 certified Quality Management System

Food Contact Compliance

Please refer to the Pall website www.pall.com/foodandbev for a Declaration of Compliance to specific National Legislation and/or Regional Regulatory requirements for food contact use.

Main Constituents

Cellulose, powdered activated carbon, diatomaceous earth (DE, Kieselguhr)

Applications

- Dechlorination of water
- Correction of off color, flavor and odors in distilled spirits
- Decolorization of sweetener and sugar syrups
- Color correction in juice and beer applications
- Gelatin decolorization and deodorization

Adsorption Capability

At an optimized flow rate, the probability of contact between the impurities and carbon particles is greater in carbon-impregnated sheets. This is due to process fluids more efficiently contacting carbon particles immobilized into a sheet matrix. Because of the depth (thickness) of the sheet, it is possible to consider the structure as being made up of a series of layers containing PAC. Having a depth of PAC and passing the fluid at an optimal flow rate through that depth enables maximum utilization of the carbon.

Macro- and mesopores can generally be regarded as the highways into the carbon particle, and are crucial for adsorption kinetics. Macropores are used for the transport, and adsorption occurs in the meso- and micropores.

Small molecules, such as methylene blue, which has a molecular weight of 319.86 Dalton, are mainly captured in micropores. Typically, over 20 g/m² methylene blue is adsorbed.

Characterization

Sheet with Protection Paper	Mass per Unit Area g/m ²	Thickness mm	Ash %	Water Permeability ¹ L/m ² /min (gal/ft ² /min)
Yes	1050	3.8	13	100 (2.5)

These figures have been determined in accordance with in-house test methods and the methods of the Technical / Analytical Work Group within the European Depth Filtration Association.

¹The permeability was measured under test conditions with clean water at 20 °C (68 °F) and a Δp of 1 bar (14.5 psi).

Regeneration

Depending upon the application and the nature of the adsorbed contaminants, AKS series filter sheets may be regenerated by means of rinsing with clean water in the forward direction. However, the achievable regeneration efficiency must be determined by monitoring filtrate quality.

Maximum backpressure during all operations is 0 bar. Any backpressure will cause damages to the sheet media.

Sanitization

Method	Temperature °C (°F)	Maximum Differential Pressure bar (psi)	Time ³ / Cycle min
Steam ²	125 (257)	0.5 (7.2)	20
Hot Water	90 (194)	1 (14.5)	30

² Max. 2 steam cycles

³ The actual time required may vary as a function of the process conditions.

General Instructions for Use

In order to maximize the required adsorption of impurities, particle filtration must occur upstream of carbon-impregnated filter sheets.

Filtration Guidelines

Typical flux rates used on food and beverage fluids are 150-250 L/m²/h (3.7-6.2 gal/ft²/h).

Higher fluxes may be possible according to the application. Due to the various factors, which may affect the adsorption process, Pall recommends an initial scaled-down testing as a reliable method of qualifying filter performance.

For additional operating guidelines, including rinsing of sheets prior to use, please refer to instructions provided by Pall.

SUPRADisc AKS 4 Formats:

12" diameter (284 mm), 15 cells, 1.7m² area
16" diameter (410 mm), 19 cells, 4.5 m² area



Pall Corporation

Pall Food and Beverage

New York – USA
+1 516 484 3600 telephone
+1 866 905 7255 toll free

foodandbeverage@pall.com

Visit us on the Web at www.pall.com/foodandbev

Pall Corporation has offices and plants throughout the world. For Pall representatives in your area, please go to www.pall.com/contact

Please contact Pall Corporation to verify that the product conforms to your national legislation and/or regional regulatory requirements for water and food contact use.

Because of technological developments related to the products, systems, and/or services described herein, the data and procedures are subject to change without notice. Please consult your Pall representative or visit www.pall.com to verify that this information remains valid.

© Copyright 2018, Pall Corporation. Pall, Seitz and SUPRADisc are trademarks of Pall Corporation. ® Indicates a trademark registered in the USA. Filtration. Separation. Solution.SM is a service mark of Pall Corporation.